

**MARTELÉ S/A**  
AIR DRYING HAMMER EFFECT

URKI-SYSTEM

METALLIC BASE: 6060/0000 MARTELE S/A

RELATION PASTE / CONV.: 5/95

Edition: 021 2012/10

Cod: 6906000000.00000.021

### APPLICATION

#### "USE ONLY IN INDUSTRIAL FACILITIES"

Decorative surface finish and masking of surface defects in the painting of the metallic furniture, motor housings, electric panels and devices, tool boxes and general machinery.

High gloss and quick drying.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,00 - 1,02
Grinding Fineness (μ)	
Supply viscosity at 20°C	80 - 100 sec. Ford nº 4
%Solids content (weight / volume)	55 % ± 2 weight; 48 % ± 2 volume.
V.O.C. (g/l)	455
Type of product	Modified Alkyd
Colour	MARTELÉ Colour Chart

### SURFACE PREPARATION

The surface to be painted, thoroughly degreased, must be primed with F-25 Quick Drying Synthetic Primer.

### APPLICATION INSTRUCTIONS

First layer with a low flow, like a mist coat, followed by a wet coat.



65-75"  
FORD nº 4



URKISOL 400  
1-3 %



40-60 my



1-2 h. Tack free

### FEATURES OF DRY FILM

Theoretical yield (m <sup>2</sup> /l)	9 - 10 (50 my)
Gloss 60°-60°	Semi-gloss

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.