

TECHNICAL DATA SHEET


CHROMIND MIX

USE: The coating is produced on basis of high quality resin and pigments.

PURPOSE OF USE:

- for coating the internal parts of the motor vehicle (as a stand-alone coating in combination with 10% hardener and 40% thinner.
- filling in spray cans (for small repairs)
- existing instructions
- Optional: The product can be also applied without hardener putting a Clear coat on the top of it. The product only need to be thinned 60% with Chromind thinner for base.
N.B. In this case the product is not VOC compliant.

SURFACE: The surface, which we intend to paint must be sanded, clean and protected with 2K sealer.
Before the painting of the object the colour shade should be obligatory applied to test cardboard and check the suitability.

Viscosity	20 – 22 sec. DIN 53211 Φ 4mm/ 20°C
Data for a gun	1,2 – 1,4 mm 2 – 5 bars
Coat thickness	2x = 17 - 23 μ m
	EU limit value VOC for this type of products (category II B (e)) in the form, which is ready for application is 840 g/l VOC of this product, prepared for use is 810 g/l.

