



MOBIHEL®

Produced in HELIOS Tovarna barv, lakov in umetnih smol Količevo d.o.o.
Količevo 65, 1230 Domžale, Slovenia
T +386 1 722 40 00
F +386 1 722 43 10
E info@helios.si
www.helios.si

TECHNICAL DATA SHEET










MOBIHEL PE putty with glass fibres

Use: *Two-component polyester coarse levelling out mass to even out bigger irregularities and small rust through holes (up to 1 cm²) on steel sheet metal.
At sand-blasting of this putty it may happen, that a fibre stands up, therefore after sand-blasting it is obligatory necessary to apply a thin coat of MOBIHEL PE putty in order to get a smooth surface.*

Surface: - *sand-blasted and cleaned steel sheet metal and polyester*

Colour shade: *grey*

ONLY FOR PROFESSIONAL USE!

	<p><i>Pot life</i> 7 – 11 min. / 20°C</p>
	
	<p>20 – 30 min. / 20°C</p>
	<p>5 min.</p>
	<p>P 80 - 120</p>
	<p>MOBIHEL PE putty</p>
	<p>FURTHER TREATMENT: All 2K sealers from programme MOBIHEL</p>
	<p>EU limit value VOC for this type of products (category II B (a)) in the form, which is ready for application is 250 g/l VOC of this product, prepared for use is 170 g/l.</p>
	<p>1 year</p>